



IN THE SPECIFICATION:

At page 4, lines 8-15:

The present invention also provides a laminated carrier film comprising a drawn polyester film having a thickness of 5 to 300  $\mu\text{m}$  and a film comprising a fluororesin laminated on at least one side of the drawn polyester film, the carrier film having a difference between a maximum thickness and a minimum thickness (R) of 5 $\mu\text{m}$  or smaller, wherein R is measured along a 10 cm-long line starting at an arbitrary point on a surface of the laminated film with a continuous-mode thickness meter provided with a tip having a diameter of 5 mm.